

Average Weight: 10.8689g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.694500	6.390
	Silicon	7440-21-3	100.00		0.694500	
Solder Bump					0.036115	0.332
	Tin	7440-31-5	63.00		0.022753	
	Lead	7439-92-1	37.00		0.013363	
Underfill					0.074000	0.681
	Silica	60676-86-0	70.00		0.051800	
	Epoxy Resin A	9003-36-5	20.00		0.014800	
	Epoxy Resin B	25068-38-6	3.00		0.002220	
	Hardener	19900-65-3	7.00		0.005180	
Heat Spreader					6.000000	55.203
	Copper	7440-50-8	99.90		5.994000	
	Nickel	7440-02-0	0.10		0.006000	
Heat Spreader Adhesive					0.130000	1.196
	Organopolysiloxane mixture	NA	100.00		0.130000	
Substrate					2.975310	27.375
	Copper	7440-50-8	47.52	Metal layer	1.390779	
	Nickel	7440-02-0	0.52	Metal layer	0.014877	
	Gold	7440-57-5	0.11	Metal layer	0.003273	
	Glass fiber	NA	10.35		0.309432	
	Halogen fire retardant	NA	5.30		0.156085	
	BT (core)	NA	27.50		0.833087	
	Solder mask	NA	8.70		0.267778	
Solder Balls					0.959000	8.823
	Tin	7440-31-5	63.00		0.60417	
	Lead	7439-92-1	37.00		0.35483	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
3/23/06	1.0	Initial Xilinx release.
7/07/06	1.1	100% Material Declaration.
9/27/06	1.2	Updated component descriptions.
7/20/10	1.3	Updated Heat Spreader substance description.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.