

Average Weight: 10.9443 g

Component	Substance Description	CAS# or Description	% of Component	Use in Product	Component Weight/ Substance Weight (in grams)	Component % of Total
Silicon Die					0.321700	2.939%
	Silicon	7440-21-3	100.00		0.321700	
Die Attach Material					0.002500	0.023%
	Silver	7440-22-4	75.00		0.001875	
	Resin	Trade Secret	25.00		0.000625	
Mold Compound					0.646000	5.903%
	Resin	Trade Secret	26.00		0.167960	
	Silica	60676-86-0	74.00	Filler	0.478040	
Gold Wire					0.024000	0.219%
	Gold	7440-57-5	100.00		0.024000	
Dam					0.014600	0.133%
	Damming Material	Trade Secret	100.00		0.014600	
Solder Balls					1.752000	16.008%
	Tin (Sn)	7440-31-5	63.00		1.103760	
	Lead (Pb)	7439-92-1	37.00		0.648240	
Laminate					0.790000	7.218%
	BT (core)	Trade Secret	60.89		0.481000	
	Solder mask (EP)	Trade Secret	21.27		0.168000	
	Copper (Cu)	7440-50-8	15.44		0.122000	
	Nickel (Ni)	7440-02-0	1.77		0.014000	
	Gold (Au)	7440-57-5	0.63		0.005000	
Heat Spreader					7.064500	64.550%
	Copper (Cu)	7440-50-8	97.50		6.887888	
	Iron (Fe)	7439-89-6	2.35	Metal Layer	0.166016	
	Phosphorus (P)	7723-14-0	0.03	Metal Layer	0.002119	
	Zinc (Zn)	7440-66-6	0.12	Metal Layer	0.008477	
Heat Spreader Adhesive					0.329000	3.006%
	Nickel (Ni)	7440-02-0	100.00		0.329000	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
04/06/06	1.0	Initial Xilinx release.
07/12/06	1.1	100% Material Declaration
09/28/06	1.2	Update component directory
01/08/07	1.2.1	Corrected Gold Wire CAS# entry
10/05/11	1.3	Update component weights and descriptions

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.