



PK464 (v1.1) September 28, 2012

100% Material Declaration Data Sheet FFG1924

Average Weight: 28.1626 g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die (FPGA)					0.785000	2.787
	Doped silicon (Si)	7440-21-3	100.00	Basis	0.785000	
Solder Bump					0.064920	0.231
	Tin (Sn)	7440-31-5	63.00	Basis	0.040900	
	Lead (Pb)	7439-92-1	37.00	Basis	0.024020	
Die Underfill					0.100000	0.355
	Bisphenol F-type liquid epoxy resin	9003-36-5	20.00	Basis	0.020000	
	Phenolic resin	Trade secret	15.00	Basis	0.015000	
	Bisphenol A-type liquid epoxy resin	25068-38-6	5.00	Basis	0.005000	
	Amine type accelerator	Trade secret	5.00	Basis	0.005000	
	Silicon dioxide	60676-86-0	51.50	Basis	0.051500	
	Carbon black	1333-86-4	1.00	Basis	0.001000	
	Additives	Trade secret	2.50	Basis	0.002500	
Solder Balls					1.610000	5.717
	Tin (Sn)	7440-31-5	96.50	Base metal	1.553650	
	Silver (Ag)	7440-22-4	3.00	Base metal	0.048300	
	Copper (Cu)	7440-50-8	0.50	Base metal	0.008050	
Substrate					7.128284	25.311
	Cu	7440-50-8	36.17	Main material	2.578435	
	Tin	7440-31-5	0.59	Main material	0.042230	
	Lead	7439-92-1	0.19	Main material	0.013254	
	Silver	7440-22-4	0.01	Main material	0.000657	
	BT Core	N/A	34.66	Main material	2.470500	
	ABF	N/A	27.27	Main material	1.944000	
	Soldermask	N/A	1.11	Main material	0.079208	

© Copyright 2011-2012 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Solder Paste					0.028400	0.101
	Tin (Sn)	7440-31-5	96.50	Basis	0.027406	
	Silver (Ag)	7440-22-4	3.00	Basis	0.000852	
	Copper (Cu)	7440-50-8	0.50	Basis	0.000142	
Capacitor					0.056000	0.199
	Ceramic (BaTiO3 type)	Trade secret	61.80	Ceramic	0.034608	
	Inner electrode (Ni)	7440-02-0	27.00	Inner electrode	0.015120	
	Outer electrode (Cu)	7440-50-8	9.90	Outer electrode	0.005544	
	Plating1 (Ni)	7440-02-0	0.40	Plating1	0.000224	
	Plating2 (Sn)	7440-31-5	0.90	Plating2	0.000504	
Capacitor					0.062400	0.222
	Ceramic (BaTiO3 type)	Trade secret	67.40	Ceramic	0.042058	
	Inner electrode (Ni)	7440-02-0	17.00	Inner electrode	0.010608	
	Outer electrode (Cu)	7440-50-8	13.80	Outer electrode	0.008611	
	Plating1 (Ni)	7440-02-0	0.50	Plating1	0.000312	
	Plating2 (Sn)	7440-31-5	1.30	Plating2	0.000811	
Capacitor					0.031200	0.111
	Ceramic (BaTiO3 type)	Trade secret	64.94	Ceramic	0.020261	
	Inner electrode (Ni)	7440-02-0	19.20	Inner electrode	0.005990	
	Outer electrode (Cu)	7440-50-8	14.07	Outer electrode	0.004390	
	Plating1 (Ni)	7440-02-0	0.51	Plating1	0.000159	
	Plating2 (Sn)	7440-31-5	1.28	Plating2	0.000399	
Capacitor					0.008400	0.034
	Ceramic (BaTiO3 type)	Trade secret	66.00	Ceramic	0.005544	
	Inner electrode (Ni)	7440-02-0	2.67	Inner electrode	0.000224	
	Outer electrode (Cu)	7440-50-8	23.33	Outer electrode	0.001960	
	Plating1 (Ni)	7440-02-0	2.33	Plating1	0.000196	
	Plating2 (Sn)	7440-31-5	5.67	Plating2	0.000476	
Heat Sink					18.108000	64.298
	Copper (Cu)	7440-50-8	99.15	Main material	17.954082	
	Nickel (Ni)	7440-02-0	0.85	Main material	0.153918	
Heat Sink Adhesive					0.180000	0.639
	Aluminum oxide	1344-28-1	70.00	Main material	0.126000	
	Zinc oxide	1314-13-2	15.00	Main material	0.027000	
	Organic Silicon compound	Trade secret	15.00	Main material	0.027000	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
03/04/11	1.0	Initial Xilinx release.
09/28/12	1.1	Updated Substrate Component

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.