

# 100% Material Declaration Data Sheet for 7 Series FLG1930/FLG1931 Package

**Average Weight: 27.8237 g**

Component	Substance Description	CAS# or Description	% of Component	Use in Product	Component Weight/ Substance Weight (in grams)	Component % of Total
<b>Silicon Die</b>					<b>0.751570</b>	<b>2.701%</b>
	Silicon	7440-21-3	100.00	Basis	0.751570	
<b>Micro Bump</b>					<b>0.038070</b>	<b>0.137%</b>
	Copper	7440-50-8	54.80	Metal	0.020863	
	Nickel	7440-02-0	22.69	Metal	0.008637	
	Tin	7440-31-5	21.87	Metal	0.008326	
	Silver	7440-22-4	0.64	Metal	0.000244	
<b>Micro-Bump Underfill</b>					<b>0.037920</b>	<b>0.136%</b>
	Amorphous Silica	Trade Secret	46.87	Filler	0.017775	
	Amine Compound	Trade Secret	20.84	Glue	0.007900	
	Epoxy Resin A	Trade Secret	15.63	Glue	0.005925	
	Epoxy Resin B	Trade Secret	15.63	Glue	0.005925	
	Epoxy Resin C	Trade Secret	1.04	Glue	0.000395	
<b>Moulding Compound</b>					<b>0.095451</b>	<b>0.343%</b>
	Silica Filler	Trade Secret	86.02	Filler	0.082108	
	Epoxy Resin	Trade Secret	8.60	Glue	0.008211	
	Hardener Resin	Trade Secret	5.38	Glue	0.005132	
<b>Interposer Die</b>					<b>0.176402</b>	<b>0.634%</b>
	Silicon	7440-21-3	100.00	Basis	0.176402	
<b>C4 Bump</b>					<b>0.106580</b>	<b>0.383%</b>
	Copper	7440-50-8	5.41	Metal	0.005763	
	Nickel	7440-02-0	3.22	Metal	0.003435	
	Tin	7440-31-5	57.53	Metal	0.061317	
	Lead	7439-92-1	33.84	Metal	0.036065	
<b>Solder Paste</b>					<b>0.030860</b>	<b>0.111%</b>
	Bismuth	7440-69-9	56.30	Metal	0.017370	
	Tin	7440-31-5	42.80	Metal	0.013210	
	Silver	7440-22-4	0.90	Metal	0.000280	

100% Material Declaration Data Sheet – 7 Series FLG1930

Component	Substance Description	CAS# or Description	% of Component	Use in Product	Component Weight/ Substance Weight (in grams)	Component % of Total
<b>C4 Underfill</b>					<b>0.135000</b>	<b>0.485%</b>
	Bisphenol F/ Epichlorohydrin Copolymer	9003-36-5	24.00	Basis	0.032400	
	Phenolic Resin	Trade Secret	19.00	Basis	0.025650	
	Bisphenol A Type Liquid Epoxy Resin	25068-38-6	4.00	Basis	0.005400	
	Amine Type Accelerator	Trade Secret	5.00	Basis	0.006750	
	Silicon Dioxide	60676-86-0	44.10	Basis	0.059535	
	Carbon Black	1333-86-0	0.90	Basis	0.001215	
	Additives	Trade Secret	3.00	Additives	0.004050	
<b>Lid</b>					<b>15.676440</b>	<b>56.342%</b>
	Copper	7440-50-8	99.64	Main Material	15.621060	
	Nickel	7440-02-0	0.36	Main Material	0.055380	
<b>Lid Adhesive</b>					<b>0.050000</b>	<b>0.180%</b>
	Silica, Vitreous	60676-86-0	60.00	Main Material	0.030000	
	Unsaturate Cyclic Siloxane Polymer	Unknown	30.00	Main Material	0.015000	
	Hydrocarbon Synthetic Rubber	Proprietary	8.00	Main Material	0.004000	
	Boron Nitride	Proprietary	1.00	Main Material	0.000500	
	Carbon Black	1333-86-4	0.50	Main Material	0.000250	
	Toluene	108-88-3	0.50	Main Material	0.000250	
<b>Lid TIM</b>					<b>0.270000</b>	<b>0.970%</b>
	Aluminum Oxide	1344-28-1	85.00	Main Material	0.229500	
	Zinc Oxide	1314-13-2	5.00	Main Material	0.013500	
	Silicone	Confidential	9.00	Main Material	0.024300	
	Others	Confidential	1.00	Main Material	0.002700	
<b>Solder Ball</b>					<b>1.911630</b>	<b>6.871%</b>
	Tin	7440-31-5	96.50	Main Material	1.844720	
	Silver	7440-22-4	3.00	Main Material	0.057350	
	Copper	7440-50-8	0.50	Main Material	0.009560	
<b>Capacitor 1</b>					<b>0.054901</b>	<b>0.197%</b>
	BaTiO3 Type	12047-27-7	70.60	Ceramic	0.038761	
	Nickel	7440-02-0	6.70	Inner Electrode	0.003678	
	Copper	7440-50-8	20.10	Outer Electrode	0.011035	
	Nickel	7440-02-0	0.80	Plating 1	0.000439	
	Tin	7440-31-5	1.80	Plating 2	0.000988	

100% Material Declaration Data Sheet – 7 Series FLG1930

Component	Substance Description	CAS# or Description	% of Component	Use in Product	Component Weight/ Substance Weight (in grams)	Component % of Total
<b>Capacitor 2</b>					<b>0.030324</b>	<b>0.109%</b>
	BaTiO3 Type	12047-27-7	61.70	Ceramic	0.018710	
	Nickel	7440-02-0	4.89	Inner Electrode	0.001483	
	Indium Tin Oxide	50926-11-9	18.30	Outer Electrode	0.005549	
	Copper	7440-50-8	13.40	Outer Electrode	0.004063	
	Nickel	7440-02-0	0.49	Plating 1	0.000149	
	Tin	7440-31-5	1.22	Plating 2	0.000370	
<b>Capacitor 3</b>					<b>0.003595</b>	<b>0.013%</b>
	BaTiO3	12047-27-7	66.00	Ceramic	0.002373	
	Nickel	7440-02-0	2.67	Inner Electrode	0.000096	
	Copper	7440-50-8	23.33	Outer Electrode	0.000839	
	Nickel	7440-02-0	2.33	Plating 1	0.000084	
	Tin	7440-31-5	5.67	Plating 2	0.000204	
<b>Capacitor 4</b>					<b>0.0149898</b>	<b>0.054%</b>
	BaTiO3 Type	12047-27-7	70.00	Ceramic	0.010429	
	Copper	7440-50-8	21.95	Inner Electrode	0.003265	
	Nickel	7440-02-0	1.21	Outer Electrode	0.000184	
	Nickel	7440-02-0	2.75	Plating 1	0.000408	
Tin	7440-31-5	4.09	Plating 2	0.000612		
<b>Substrate</b>					<b>8.440067</b>	<b>30.334%</b>
	Copper	7440-50-8	48.52		4.094700	
	Tin	7440-31-5	0.11		0.009250	
	Lead	7439-92-1	0.16		0.013598	
	Silver	7440-22-4	0.48		0.040569	
	BT Core	N/A	39.44		3.328950	
	ABF	N/A	10.30		0.869350	
Solder Mask	Trade Secret	0.99		0.083650		

## Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
09/16/13	1.0	Initial Xilinx release.
08/06/16	1.1	Update to reference FLG1931 package

---

## Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.