



100% Material Declaration Data Sheet for 7 Series FFG1928

PK656 (v1.0) May 23, 2014

Average Weight: 24.9750g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.828955	3.319
	Silicon (Si)	7440-21-3	100.00	Basis	0.828955	
Solder Bump					0.038857	0.156
	Tin (Sn)	7440-31-5	63.00	Basis	0.024480	
	Lead (Pb)	7439-92-1	37.00	Basis	0.014377	
Solder Paste					0.014100	0.056
	Tin (Sn)	7440-31-5	96.50	Basis	0.013607	
	Silver (Ag)	7440-22-4	3.00	Basis	0.000423	
	Copper (Cu)	7440-50-8	0.50	Basis	0.000071	
Capacitor 1					0.041280	0.165
	BaTiO3 type	12047-27-7	70.60	Ceramic	0.029144	
	Nickel (Ni)	7440-02-0	6.70	Inner electrode	0.002766	
	Copper (Cu)	7440-50-8	20.10	Outer electrode	0.008297	
	Nickel (Ni)	7440-02-0	0.80	Plating 1	0.000330	
	Tin (Sn)	7440-31-5	1.80	Plating 2	0.000743	
Capacitor 2					0.015200	0.061
	BaTiO3 type	12047-27-7	61.70	Ceramic	0.009378	
	Nickel (Ni)	7440-02-0	4.89	Inner electrode	0.000743	
	Indium tin oxide	50926-11-9	18.30	Outer electrode	0.002782	
	Copper (Cu)	7440-50-8	13.40	Outer electrode	0.002037	
	Nickel (Ni)	7440-02-0	0.49	Plating 1	0.000074	
	Tin (Sn)	7440-31-5	1.22	Plating 2	0.000185	
Capacitor 3					0.012000	0.048
	BaTiO3 type	12047-27-7	66.00	Ceramic	0.007920	
	Nickel (Ni)	7440-02-0	2.67	Inner electrode	0.000320	
	Copper (Cu)	7440-50-8	23.33	Outer electrode	0.002800	
	Nickel (Ni)	7440-02-0	2.33	Plating 1	0.000280	
	Tin (Sn)	7440-31-5	5.67	Plating 2	0.000680	

© Copyright 2014 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Capacitor 4					0.011160	0.045
	BaTiO3 type	12047-27-7	51.10	Ceramic	0.005703	
	Nickel (Ni)	7440-02-0	27.00	Inner Electrode	0.003013	
	Copper (Cu)	7440-50-8	16.00	Outer Electrode	0.001786	
	Glass	65997-17-3	0.90		0.000100	
	Nickel (Ni)	7440-02-0	2.00	Plating1	0.000223	
	Tin (Sn)	7440-31-5	3.00	Plating2	0.000335	
Underfill					0.082000	0.328
	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	20.00	Basis	0.016400	
	Phenolic Resin	Trade Secret	15.00	Basis	0.012300	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.004100	
	Amine type accelerator	Trade Secret	5.00	Basis	0.004100	
	Silicon Dioxide	60676-86-0	51.50	Basis	0.042230	
	Carbon Black	1333-86-4	1.00	Basis	0.000820	
	Additives	Trade Secret	2.50	Additive	0.002050	
Lid					14.214000	56.913
	Copper (Cu)	7440-50-8	99.15	Main Material	14.093181	
	Nickel (Ni)	7440-02-0	0.85	Main Material	0.120819	
Lid Adhesive					0.340000	1.361
	Aluminium Oxide Al2O3	1344-28-1	70.00	Main Material	0.238000	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	30.00	Main Material	0.102000	
Solder Ball					1.607244	6.435
	Tin (Sn)	7440-31-5	96.50	Main Material	1.550990	
	Silver (Ag)	7440-22-4	3.00	Main Material	0.048217	
	Copper (Cu)	7440-50-8	0.50	Main Material	0.008036	
Substrate					7.770204	31.112
	Copper (Cu)	7440-50-8	44.97		3.494261	
	Tin (Sn)	7440-31-5	0.08		0.006216	
	Lead (Pb)	7439-92-1	0.11		0.008547	
	Silver (Ag)	7440-22-4	0.52		0.040405	
	BT Core	N/A	43.68		3.394025	
	ABF	N/A	9.53		0.740501	
Solder Mask	N/A	1.11		0.086249		

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
05/23/2014	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.