



PK676 (v1.0) Oct 3, 2014

100% Material Declaration Data Sheet for Spartan-3AN FG676 Cu Wire Package

Average Weight: 2.748g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die 1					0.037747	1.374%
	Silicon	7440-21-3	100.00		0.037747	
Silicon Die 2					0.002919	0.106%
	Silicon	7440-21-3	100.00		0.002919	
Die Attach					0.006967	0.254%
	Silver	7440-22-4	77.50		0.005399	
	Bismaleimide monomer	Trade secret	15.00		0.001045	
	Acrylate monomer	Trade secret	7.50		0.000523	
Film					0.000017	0.001%
	Solid Epoxy Resin	NA	12.50		0.000002	
	Phenol Resin	NA	12.50		0.000002	
	Amorphous Silica	7631-86-9	35.00		0.000006	
	Synthetic Rubber	NA	40.00		0.000007	
Mold Compound					1.421610	51.729%
	Epoxy Resin	Trade secret	9.00		0.127945	
	Silica(Amorphous) A	60676-86-0	72.45		1.029956	
	Silica(Amorphous) B	7631-86-9	15.00		0.213242	
	Metal Hydroxide	Trade secret	3.00		0.042648	
	Carbon black	1333-86-4	0.55		0.007819	
Gold Wire					0.000233	0.009%
	Gold	7440-57-5	99.048		0.000231	
	Palladium	7440-05-3	0.95		0.000002	
	Calcium	7440-70-2	0.002		0.000000	
Copper Wire					0.007971	0.290%
	Copper	7440-50-8	98.25		0.007832	
	Palladium	7440-05-3	1.75		0.000139	
Solder Ball					0.643415	23.412%
	Tin	7440-31-5	63.00		0.405351	
	Lead	7439-92-1	37.00		0.238064	

© Copyright 2014 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

100% Material Declaration Data Sheet for Spartan-3AN FG676 Cu Wire

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Substrate					0.627301	22.826%
	Gold	7440-57-5	58.41		0.366400	
	Nickel	7440-02-0	0.29		0.001795	
	Copper Plating	7440-50-8	2.20		0.013810	
	Copper Foil	7440-50-8	14.39		0.090263	
	Continuous Filament Fiber Glass	65997-17-3	5.63		0.035328	
	BT Core	7440-50-8	6.36		0.039886	
	Pre-preg Fabric	NA	4.36		0.027350	
Solder mask	14807-96-6 7727-43-7 7631-86-9 34590-94-8 91-20-3 85954-11-6	8.36		0.052469		

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
10/03/2014	1.0	Xilinx Initial Release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.