



100% Material Declaration Data Sheet for UltraScale FFVA1156

PK692 (v1.0) December 15, 2014

Average Weight: 11.640g

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Silicon Die					0.474641	4.078%
	Silicon (Si)	7440-21-3	100.00	Basis	0.474641	
Solder Bump					0.022556	0.194%
	Tin (Sn)	7440-31-5	98.20	Basis	0.022150	
	Silver (Ag)	7440-22-4	1.80	Basis	0.000406	
Solder Paste					0.010880	0.093%
	Tin (Sn)	7440-31-5	96.50	metal	0.010499	
	Silver (Ag)	7440-22-4	3.00	metal	0.000326	
	Copper (Cu)	7440-50-8	0.50	metal	0.000054	
Capacitor 1					0.032000	0.275%
	Barium oxide	1304-28-5	30.22	Ceramic	0.009670	
	Titanium dioxide	13463-67-7	15.11	Ceramic	0.004835	
	Misc.	trade secret	5.04	Ceramic	0.001613	
	Nickel (Ni)	7440-02-0	33.44	Inner electrode	0.010701	
	Copper (Cu)	7440-50-8	11.87	Outer electrode	0.003798	
	Silicon dioxide	7631-86-9	1.06	Outer electrode	0.000339	
	Boric oxide	1303-86-2	0.26	Outer electrode	0.000083	
	Nickel (Ni)	7440-02-0	0.81	Nickel Plating Layer	0.000259	
	Tin (Sn)	7440-31-5	2.19	Tin Plating Layer	0.000701	
Capacitor 2					0.008720	0.075%
	Barium oxide	1304-28-5	31.67	Ceramic	0.002762	
	Titanium dioxide	13463-67-7	15.83	Ceramic	0.001380	
	Misc.	trade secret	5.28	Ceramic	0.000460	
	Nickel (Ni)	7440-02-0	26.67	Inner electrode	0.002326	
	Copper (Cu)	7440-50-8	15.10	Outer electrode	0.001317	
	Silicon dioxide	7631-86-9	1.34	Outer electrode	0.000117	
	Boric oxide	1303-86-2	0.33	Outer electrode	0.000029	
	Nickel (Ni)	7440-02-0	1.00	Nickel Plating Layer	0.000087	
	Tin (Sn)	7440-31-5	2.78	Tin Plating Layer	0.000242	

© Copyright 2014 Xilinx, Inc. XILINX, the Xilinx logo, Virtex, Spartan, ISE, and other designated brands included herein are trademarks of Xilinx in the United States and other countries. All other trademarks are the property of their respective owners

Component	Substance Description	CAS Number or Description	Percentage of Component	Use in Product	Component Weight/ Substance Weight (grams)	Component Percent of Total
Underfill					0.062000	0.533%
	Bisphenol F type liquid epoxy resin	9003-36-5	15.00	Basis	0.009300	
	1,6-Bis(2,3-epoxypropoxy)naphthalene	27610-48-6	10.00	Basis	0.006200	
	Bisphenol A type liquid epoxy resin	25068-38-6	5.00	Basis	0.003100	
	Amine type hardener	trade secret	10.00	Basis	0.006200	
	Silicon dioxide	60676-86-0	58.00	Filler	0.035960	
	Carbon black	1333-86-4	1.00	Color agent	0.000620	
	Additives	trade secret	1.00	Additives	0.000620	
Lid					5.040000	43.299%
	Copper (Cu)	7440-50-8	98.35	Main Material	4.956840	
	Nickel (Ni)	7440-02-0	1.65	Main Material	0.083160	
Lid Adhesive					0.160000	1.375%
	Aluminium Oxide Al ₂ O ₃	1344-28-1	80.00	Main Material	0.128000	
	Dimethyl siloxane, dimethylvinyl-terminated	68083-19-2	20.00	Main Material	0.032000	
Solder Ball					0.965683	8.296%
	Tin (Sn)	7440-31-5	96.50	Main Material	0.931884	
	Silver (Ag)	7440-22-4	3.00	Main Material	0.028970	
	Copper (Cu)	7440-50-8	0.50	Main Material	0.004828	
Substrate					4.863520	41.783%
	Copper (Cu)	7440-50-8	54.71		2.660626	
	Tin (Sn)	7440-31-5	0.73		0.035474	
	Lead (Pb)	7439-92-1	0.00		0.000005	
	Silver (Ag)	7440-22-4	0.02		0.001103	
	BT Core	N/A	35.29		1.716164	
	ABF	N/A	8.06		0.391828	
	Solder Mask	N/A	1.20		0.058319	

Revision History

The following table shows the revision history for this document.

Date	Version	Description of Revisions
12/15/2014	1.0	Initial Xilinx release

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers (“Contractors”). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.