



PK800 (v1.0) Jun 23, 2016

## 100% Material Declaration Data Sheet for FBG676

**Average Weight : 2.7985 g**

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight ( in grams)	Component % of total
Silicon Die					<b>0.237267</b>	<b>8.478%</b>
	Silicon	NA 7440-21-3	100	basis	0.237267	
Bump					<b>0.011261</b>	<b>0.402%</b>
	Tin	7440-31-5	63.00	basis	0.007094	
	Lead	7439-92-1	37.00	basis	0.004167	
Underfill					<b>0.030000</b>	<b>1.072%</b>
	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	20.00	basis	0.006000	
	Phenolic resin	trade secret	15.00	basis	0.004500	
	Bisphenol A type liquid epoxy	25068-38-6	5.00	basis	0.001500	
	Amine type accelerator	trade secret	5.00	basis	0.001500	
	Silicon dioxide	60676-86-0	51.50	filler	0.015450	
	Carbon black	1333-86-4	1.00	color agent	0.000300	
Additives	trade secret	2.50	additives	0.000750		
Solder ball					<b>0.564707</b>	<b>20.179%</b>
	Tin	7440-31-5	96.50	basis	0.544942	
	Silver	7440-22-4	3.00	basis	0.016941	
	Copper	7440-50-8	0.50	basis	0.002824	
Substrate					<b>1.955293</b>	<b>69.869%</b>
	Copper	7440-50-8	36.45		0.712704	
	Tin	7440-31-5	0.91		0.017793	
	Lead	7439-92-1	0.20		0.003911	
	Silver	7440-22-4	0.02		0.000391	
	Core	N/A	48.71		0.952423	
	ABF	N/A	11.22		0.219384	
	Solder Mask	N/A	2.49		0.048687	

### Revision History

Date	Version	Description of Revisions
6/23/2016	1.0	Initial Xilinx release.

### Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.