



PK922 (v1.0) August 30, 2017

100% Material Declaration Data Sheet for UltraScale + FLVA/FLVB/FLVC 2104

Average Weight : 31.6843 g

Component	Substance Description	CAS # or Description	% of component	Use in product	Component weight / substance weight (in grams)	Component % of total
Silicon die	Silicon	7440-21-3	100.00	basis	0.659525	2.08%
					0.659525	
Micro-bump	Copper	7440-50-8	54.80	metal	0.023176	0.13%
	Nickel	7440-02-0	22.69	metal	0.009594	
	Tin	7440-31-5	21.87	metal	0.009250	
	Silver	7440-22-4	0.64	metal	0.000272	
					0.038875	
Micro-bump underfill	Amorphous silica	trade secret	46.87	Filler	0.018220	0.12%
	Amine compound	trade secret	20.84	Glue	0.008100	
	Epoxy resin compound-A	trade secret	15.63	Glue	0.006075	
	Epoxy resin compound-B	trade secret	15.63	Glue	0.006075	
	Epoxy resin compound-C	trade secret	1.04	Glue	0.000405	
					0.096193	
Mold compound	Silica filler	trade secret	86.02	Filler	0.082747	0.30%
	Epoxy resin	trade secret	8.60	Glue	0.008275	
	Hardener resin	trade secret	5.38	Glue	0.005172	
Interposer die	Silicon	7440-21-3	100.00	basis	0.178526	0.56%
C4 Bump	Copper	7440-50-8	70.73	metal	0.001464	0.01%
	Tin	7440-31-5	28.53	metal	0.000591	
	Silver	7440-22-4	0.75	metal	0.000015	
					0.027087	
Solder Paste	Tin	7440-31-5	96.5	metal	0.026139	0.09%
	Silver	7440-22-4	3	metal	0.000813	
	Copper	7440-50-8	0.5	metal	0.000135	
C4 Underfill	Bisphenol F/ epichlorohydrin copolymer	9003-36-5	22	basis	0.025300	0.36%
	Silicon dioxide	60676-86-0	72	basis	0.082800	
	Carbon black	1333-86-4	1	basis	0.001150	
	Additives	trade secret	5	Additive	0.005750	
Lid	Copper	7440-50-8	99.64	Main material	17.338205	54.92%
	Nickel	7440-02-0	0.36	Main material	0.062643	
Lid Adhesive	Silica, Vitreous	60676-86-0	60	Main material	0.030000	0.16%
	Unsaturated Cyclic	trade secret	30	Main material	0.015000	
	Hydrocarbon Synthetic	Proprietary	8	Main material	0.004000	
	Boron Nitride	Proprietary	1	Main material	0.000500	
	Carbon Black	1333-86-4	0.5	Main material	0.000250	
	Toluene	108-88-3	0.5	Main material	0.000250	
					0.170000	
Lid TIM	Aluminum oxide	1344-28-1	85	Main material	0.144500	0.54%
	Zinc oxide	1314-13-2	5	Main material	0.008500	
	Silicone	Confidential	9	Main material	0.015300	
	Others	Confidential	1	Main material	0.001700	
Solder Ball	Tin	7440-31-5	96.5	Main material	1.687481	5.52%
	Silver	7440-22-4	3	Main material	0.052461	
	Copper	7440-50-8	0.5	Main material	0.008743	
Capacitor 1					0.054400	0.17%
	Titanium Dioxide	13463-67-7	15.11		0.008220	
	Misc		5.04		0.002742	
	Nickel	7440-02-0	33.44	Inner electrode	0.018191	
	Copper	7440-50-8	11.87	Out electrode	0.006457	
	Silicon Dioxide	7631-86-9	1.06		0.000577	
	Diboron trioxide; Boric	1303-86-2	0.26		0.000141	
	Nickel	7440-02-0	0.81	Plating1	0.000441	
	Tin	7440-31-5	2.19	Plating2	0.001191	
	Other		30.22		0.016440	
Capacitor 2	BaTiO3 type	12047-27-7	51.10	Ceramic	0.008997	0.06%
	Copper	7440-50-8	27.00	Inner electrode	0.004754	
	Nickel	7440-02-0	16.90	Out electrode	0.002976	
	Nickel	7440-02-0	2.00	Plating1	0.000352	
	Tin	7440-31-5	3.00	Plating2	0.000528	
Substrate					11.083183	34.98%
	Copper	7440-50-8	34.94		3.872646	
	Tin	7440-31-5	0.36		0.039899	
	Silver	7440-22-4	0.01		0.001108	
	Core	N/A	48.86		5.415062	
	ABF	N/A	14.66		1.624795	
Solder Mask	N/A	1.17		0.129673		

Revision History

Date	Version	Description of Revisions
8/30/2017	1.0	Initial Xilinx release.

Notice of Disclaimer

Xilinx regards this materials data to be correct but makes no guarantee as to its accuracy or completeness, including, but not limited to, with respect to its compliance with applicable environmental laws and regulations. Xilinx subcontracts the production, test and assembly of hardware devices to independent third-party vendors and materials suppliers ("Contractors"). All data provided hereunder is based on information received from Contractors. Xilinx has not independently verified the accuracy or completeness of this information which is provided solely for your reference in connection with the use of Xilinx products.